

Product Data Sheet
QC-8700
Engineered Structural Composite (ESC) Molding Compound

QC-8700 is a vinyl ester ESC molding compound designed for compression molding of components requiring high structural strength. It exhibits unusual toughness, and is suggested for applications subject to impacts and rough handling. QC-8700 is also suggested for applications requiring excellent fatigue resistance. It exhibits better temperature resistance than QC-8800.

TYPICAL PROPERTIES -- UNCURED

Form Festooned Sheet 48" width, Shelf Life: @75°F 2 months
0.125"
Color Black Glass Fiber Content 63%
Glass Fiber Length 1.0 inch

TYPICAL PROPERTIES -- CURED

<u>Test</u>	<u>Procedure</u>	<u>Value</u>
Specific Gravity	ASTM D-792	1.87
Shrinkage, inch/inch (mm/mm)	ASTM D-955	0.001 (0.001)
Hardness, Barcol	ASTM D-2583	68
Water Absorption, %	ASTM D-570	0.08
Flexural Strength, psi (MPa) ¹	ASTM D-790	92,000 (633)
Flexural Modulus, psi (GPa) ¹	ASTM D-790	3.0x10 ⁶ (20.6)
Tensile Strength, psi (MPa) ¹	ASTM D-638	52,000 (358)
Tensile Modulus, psi (GPa) ¹	ASTM D-638	3.9x10 ⁶ (26.8)
Poisson's Ratio	ASTM D-638	0.38
Izod Impact, notched, ft.lb./in. (J/M)	ASTM D-256	33 (1760)

Molding Suggestions -- QC-8700 can be molded over a range of temperatures and pressures. For part thickness of 0.5 inches or less, molding temperatures of 270° to 300°F are suggested as a starting point, with molding pressure of 300 to 1000 psi. For molding thicker sections, the molding temperature should be reduced. Cure time will depend on molding temperature and part thickness. A 0.25 inch section will cure in 3 to 5 minutes at 280°F.

Precautions -- QC-8700 contains glass fibers and styrene monomer. Use only in areas with good ventilation. Handle carefully in order to minimize skin contact. See Material Safety Data Sheet for additional information.

WARRANTY -- The above information is offered for your consideration, investigation, and verification. No warranty, expressed or implied, is given, nor is freedom from any patents owned by Quantum Composites, Inc. or others implied. Final determination of the suitability of this material is the sole responsibility of the buyer. Contact our sales representative for assistance in developing procedures to fit individual requirements.

¹Tensile and Flexural Properties are determined using net shape molded specimens. Values obtained on cut specimens will typically be lower.